

DensGlass Sheathing Board

Product Description

DensGlass Sheathing is a high performance, A1 Fire Rated sheathing board that consists of a fibreglass mat with a gypsum core, designed to provide a high degree of protection from the elements in external cladding constructions. Widely recognised by the GOLD colour, DensGlass fibreglass mat gypsum sheathing board, has an exemplary track record that spans more than 30 years in the US market place and now available in UK exclusively from Benx.



Material Composition	Non-combustible glass-fibre reinforced; moisture resistant gypsum fibreboard encased by hydrophobic-treated glass mat liners.
Applications	<p>Sheathing board to:</p> <ul style="list-style-type: none"> Rainscreen cladding Masonry facades Fibre Cement sidings - RCM Supertech Weatherboard Timber cladding External Wall Insulation System
Appearance	The unique gold fibre to DensGlass Sheathing provides easy differentiation for this sheathing board with a track record of over 30 years, with it's ability to resist moisture and UV light.

Dimensional Conformity	
Nominal Thickness	12.7mm
Nominal Length	2400mm
Nominal Width	1200mm
Weight per m2	9.3kg

Technical Information	Value/Unit	Applicable standard
Reaction to Fire	Class A1	BS EN 13501-1:2007
Nominal Board Density (Oven Dry)	≥750 kg/m ³	EN15283-1:2008 + A1:2009
Thermal Conductivity	0.21 W/mk	
Vapour Resistance	0.39 MNs/g	BS EN ISO 12572:2016
Water Vapour Transmission Rate (v)	368 g/m ² /day	BS EN ISO 12572:2016
Water Vapour Resistance Factor μ-value	6	BS EN ISO 12572:2016
Diffusion Equivalent Air Layer Thickness	0.072m	BS EN ISO 12572:2016
Surface Condition	Fleeced - Matt - Front Fleeced - Matt - Back	
Bending radius	1900mm	Reduce stud centres & double screw at board ends
Compressive Strength	min. 500 psi (3445 kPa)	
Linear expansion with moisture change	6.25 x 10 ⁻⁶ mm/mm%RH	
Coefficient of thermal expansion	15.3 x 10 ⁻⁶ mm/mm/°C	
Moisture Resistance	GM-HI Class	EN 15283-1:2008 + A1:2009
Biological/Mould Resistance	10 Level	ASTM D3273
Exposure	12 Months	

Fire Resistance Information

BS EN 1364-1 (Non Loadbearing)
Achieving 90 Minutes Integrity Insulation

BS EN 1365-1 (Loadbearing)
Achieving 90 Minutes Integrity Insulation

FOR MORE INFORMATION ON THE FIRE TESTS PLEASE CONTACT BENX TECHNICAL SERVICES

Limitations of Use

The following recommendations and limitations are important to ensure the proper use and benefits of DensGlass Sheathing. Failure to strictly adhere to such recommendations and limitations may void the limited warranty.

- DensGlass Sheathing is resistant to normal weather conditions, but it is not intended for immersion in water. Cascading roof/ floor water should be directed away from the sheathing until appropriate drainage is installed.
- Avoid any condition that will create moisture in the air and condensation on the exterior walls during periods when the exterior temperature is lower than the interior. The use of forced air heaters creates volumes of water vapor which, when not properly vented, can condense on building materials. The use of these heaters and any resulting damage is not the responsibility of the supplier. Consult heater manufacturer for proper use and ventilation.
- When DensGlass Sheathing panels are used in slanted wall applications, that portion of the wall must be temporarily protected from the elements by the use of a water-resistant barrier prior to application of the cladding.
- Do not allow water to pond or settle on sheathing. Also, exposed wall ends such as those that may be found in parapets must be covered to prevent water from infiltrating the cavity with EPDM.
- Do not laminate DensGlass Sheathing to masonry surfaces; use furring strips or framing.
- DensGlass Sheathing is not intended for roof applications.
- DensGlass Sheathing is not intended for interior or exterior tile applications.
- DensGlass Sheathing should not be used in lieu of plywood where required. Do not apply DensGlass Sheathing below DPC.
- For all installations, design details such as fasteners, sealants and control joints per system specifications must be properly installed. Openings and penetrations must be properly flashed and sealed.
- Fixings should be flush to the face of the board, not countersunk.
- When DensGlass Sheathing is used in façade construction, install boards so board joints are tightly butted together on both horizontal and vertical joints, finished with RCM FR-PRO sealant or RCM joint tape.
- As a best practice cut sheathing edges should be sealed with a proprietary sealer applied around exposed edges, such as openings, to ensure protection against water ingress.
- When installing the boards in close proximity to certain flue pipes or heat-producing appliances, follow the provisions of the national building regulations.
- Boards cannot be left exposed.

Health & Safety

See separate sheet

Handling & Storage	
Handling Storage	<p>Consider a two man lift to avoid strain.</p> <p>The boards must be stored on a firm, flat and level surface. If the boards are temporarily stored outside they must be sufficiently supported off the ground and covered by a securely anchored polythene sheet or tarpaulin to protect them from dampness, weather, contamination and mechanical damage, eg. from construction traffic. Packs of boards should be stacked no higher than two pallets from the ground for safe handling on site.</p>
Cutting Screws	<p>DensGlass Sheathing may be cut using the score and snap method, no power tools are required.</p> <p>Fixings at the required centres - RCM Gypsum Screws self-drilling screws with 1000-hour salt spray 0.7-3.0mm SFS (see fixing guide for further details) Screws to be installed flush to the board surface.</p>
Joints Recycling	<p>Lightly butt joints finished with RCM Fire Sealant or RCM tape, dependent on fire or air leakage requirements.</p> <p>Boards can be recycled - Please contact your waste provider.</p>

Disclaimer of Liability

The information supplied in this Technical Data Sheet is designed only as guidance for the safe use, storage and handling of the product. This information is correct to the best of our knowledge and belief at the date of publication however no guarantee is made to its accuracy. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process.

SPS Envirowall Ltd nor any other subsidiary of the Benx Group will be held accountable for any damage resulting from handling or from contact with the above product. This data sheet and the information it contains is not intended to supersede any terms or conditions of sale and does not constitute a specification. Nothing contained herein is to be construed as a recommendation for use in violation of any patent or applicable laws or regulations.