

RCM (Roofing and Cladding Materials Ltd)

Technical Data Sheet



ISO No. 5222

Version 1

Date prepared: January 2023

Trade Name: FR PRO

Product Name: FR PRO

Description

FR PRO is a one-part silicone sealant formulated to provide a high degree of fire resistance in a variety of joint configurations.

FR PRO exhibits excellent unprimed adhesion to most building components and is suitable for sealing a wide range of construction and expansion joints in buildings, where compartmentalisation within the building is required to control spread of fire. It cross links at room temperature to give a flexible low modulus seal which will withstand movement of 25% in constant service throughout a wide temperature range.

FR PRO exhibits excellent primerless adhesion to a wide range of substrates such as Glass, Anodised and Mill Finished Aluminium, Steel, St. Steel, rigid PVC, Concrete and other porous surfaces.

Once cured, the sealant offers superb long-term resistance to heat and fire as well as all other general weather elements.

General Applications

Typical applications include; Expansion and construction joints in walls and cladding panels, sealing of service penetrations, roofing and conservatory applications, capping sealant for bead glazing, and general sealing work.

Limitations

Silicone sealants generally should not be used in situations where abrasion from pedestrian or vehicular traffic may be encountered, or for submerged joints in porous substrates, which may permit water to reach the bond interface.

Do not use for applications subject to contact with food products.

Do not use in the manufacture of aquariums or for sealing swimming pools.

Always check to determine suitability of the sealant on any surface that may give cause for concern.

Technical Data

Specific Gravity:	1.25 – 1.30
Skimming Time:	10 minutes approx. (at 23Deg C and 50% relative humidity)
Tack Free Time:	20 minutes approx. (at 23Deg C and 50% relative humidity)
Full Cure:	Approx 2-3mm per 24Hrs (at 23Deg C and 50% relative humidity)
Shore A hardness:	20 - 28
Extrudability g/min:	55 (standard NMRPS 495A 3mm/3 bars)
Movement Accommodation:	25% (BS EN ISO 11600)

Mechanical Properties on a 2mm thick film

Modulus at 100% elongation:	0.37 Mpa
Elongation at break:	550%
Tensile strength:	1.5 Mpa

Mechanical Properties on glass slabs

Modulus at 100% elongation:	0.32 Mpa
Elongation at break:	260%
Tensile strength:	0.55 Mpa
Application Temp Range:	+5°C to +40°C
Service Temp Range:	-30°C to +150°C.
Slump Resistance:	Excellent. May be used in joints up to 25mm wide and 12mm deep.
Shelf Life:	Up to 9 months when stored in unopened cartridges under cool, dry conditions.
Life Expectancy:	When used and applied correctly the sealant will perform in excess of 20 years.
Chemical Resistance:	The cured sealant is unaffected by water, dilute acids and alkalis, soap and household detergents. Certain solvents may soften and swell the cured rubber on prolonged contact.

Fire Resistance

Fire Rating - Integrity	≥4 hours**	BS EN 1366-4
Fire Rating - Insulation	≥4 hours**	BS EN 1366-4

**It has been independently tested and achieves in certain joint configurations an integrity and insulation value in excess of 4 hours.

Application Instructions

Surfaces to which Silicone Sealant is to adhere must be clean and free from loose material, standing water or contaminants which otherwise may impair the bond.

Non-porous surfaces such as aluminium should be cleaned with a suitable product.

For applications where movement will be exhibited i.e. construction joints, the minimum joint dimensions should be 6mm x 6mm with the maximum dimensions being 25mm wide by 12mm deep. Where deeper joints are found, depth can be reduced using a suitable backer rod.

Areas of perimeter pointing where a fillet is to be applied, the minimum measurement across must be 10mm with a minimum depth of 6mm.

If conditions are suitable for application ensure joints are properly prepared, and apply sealant firmly into the joint using an application gun.

Ensure a good solid fill is achieved. Once applied, sealant can be tooled within 5 minutes to required finish.

Coverage

1 std size cartridge is sufficient to seal approximately 8.5m with a 6mm x 6mm bead.

Or 2.5 m with a joint dimension of 15mm x 8mm.

Handling & Storage

Store in dry conditions between 5°C and 25°C.

Shelf Life: Up to 9 months when stored in unopened cartridges under cool, dry conditions.

Life Expectancy: When used and applied correctly the sealant will perform in excess of 20 years.

Chemical Resistance: The cured sealant is unaffected by water, dilute acids and alkalis, soap and household detergents. Certain solvents may soften and swell the cured

Health & Safety

Consult Health and Safety Data Sheet.

Avoid contact of uncured sealant with the skin. If uncured sealant comes into contact with eyes, flush out immediately with clean water for at least 5 minutes. Consult medical advice if irritation persists

Use in a well ventilated area.

As with all chemical products, care should be taken during use and storage.

Do not eat or drink while using the product.

Keep away from children and animals.

DISCLAIMER OF LIABILITY

The information supplied in this Technical Data Sheet is designed only as guidance for the safe use, storage and handling of the product. This information is correct to the best of our knowledge and belief at the date of publication however no guarantee is made to its accuracy. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process.

SPS Envirowall Ltd nor any other subsidiary of the Benx Group will be held accountable for any damage resulting from handling or from contact with the above product. This data sheet and the information it contains is not intended to supersede any terms or conditions of sale and does not constitute a specification. Nothing contained herein is to be construed as a recommendation for use in violation of any patent or applicable laws or regulations.